



## Material data sheet

---

### EOS MaragingSteel MS1

EOS MaragingSteel MS1 is a tool steel powder intended for processing on EOS DMLS™ systems.

This document provides information and data for parts built using EOS MaragingSteel MS1 powder (EOS art.-no. 9011-0016) on the following system specifications:

- EOS DMLS™ EOS M290 system
  - Ceramic blade (2200-3013)
  - Grid nozzle (2200-5501)
  - Nitrogen atmosphere
  - IPCM extra sieving module with 63 µm mesh recommended
- EOSYSTEM:
  - EOSPRINT v 1.5 (Build9) or higher
  - HCS v 2.5.22 or higher
- EOS Parameter set: MS1\_040\_FlexM290\_200

### Description

Parts built in EOS MaragingSteel MS1 have a chemical composition following US classification 18% Ni Maraging 300, European 1.2709 and German X3NiCoMoTi 18-9-5. This kind of steel is characterized by having very good mechanical properties, and being easily heat-treatable using a simple thermal age-hardening process to obtain excellent hardness and strength.

Parts built from EOS MaragingSteel MS1 are easily machinable after the building process and can be easily post-hardened to more than 50 HRC by age-hardening at 490 °C (914 °F) for 6 hours. In both as-built and age-hardened states the parts can be machined, spark-eroded, welded, micro shot-peened, polished and coated if required. Due to the layerwise building method, the parts have a certain anisotropy, which can be reduced or removed by appropriate heat treatment – e.g. solution treatment at 940 °C (1724 °F) for 2 hours – see Technical Data for examples.

## Material data sheet

### Technical Data

#### Powder properties

The chemical composition of the powder (wt-%):

#### Material composition

Element	Min	Max
Fe	Balance	
Ni	17.00	19.00
Co	8.50	9.50
Mo	4.50	5.20
Ti	0.60	0.80
Al	0.05	0.15
Cr	-	0.50
Cu	-	0.50
C		0.03
Mn		0.10
Si		0.10
P		0.01
S		0.01

#### Max. particle size

> 63 $\mu$ m [1]

max 0.5 wt.-%

[1] Sieve analysis according to ASTM B214.

## Material data sheet

### General process data

Layer thickness	40 $\mu\text{m}$
Volume rate [2]	4.2mm <sup>3</sup> /s (15.2cm <sup>3</sup> /h)

- [2] The volume rate is a measure of build speed during laser exposure of the skin area. The total build speed depends on this volume rate and many other factors such as exposure parameters of contours, supports, up and downskin, recoating time, Home-In or LPM settings.

### Physical and chemical properties of parts\*

Part density [3]	8.0-8.1 g/cm <sup>3</sup>
Part accuracy [4]	
Small parts	Approx. $\pm 50 \mu\text{m}$
Large parts	Approx $\pm 0.1 \%$
Min. wall thickness [5]	Approx. 0.3 - 0.4 mm
Surface roughness after shot peening [6]	Ra 4-6.5 $\mu\text{m}$ ; Rz 20-50 $\mu\text{m}$

- [3] Weighing in air and water according to ISO 3369.
- [4] Based on users' experience of dimensional accuracy for typical geometries, e.g.  $\pm 50 \mu\text{m}$  when parameters can be optimized for a certain class of parts or  $\pm 0.1\%$  when building a new kind of geometry for the first time or building larger parts. Part accuracy is subject to appropriate data preparation and postprocessing.
- [5] Mechanical stability is dependent on geometry (wall height etc.) and application.
- [6] Measurement according to ISO 4287. Due to the layerwise building the roughness strongly depends on the orientation of the surface, for example sloping and curved surfaces exhibit a stair-step effect.

### Hardness in heat treated status\* [7]

Hardness Rockwell C [8]	50-57 HRC
-------------------------	-----------

- [7] Heat treatment procedure: solution treatment at 940 °C (1724 °F) for 2 hours, air cooling + ageing at 490 °C for 6 hours, air cooling.
- [8] Rockwell C (HRC) hardness measurement according to EN ISO 6508-1 on polished surface.



## Material data sheet

### Tensile properties at room temperature\* [9, 10, 11]

	Heat treated [7]	
	Horizontal	Vertical
Ultimate tensile strength, Rm	2080 MPa	2080 MPa
Yield strength, Rp0.2	2010 MPa	2000 MPa
Elongation at break, A	4 %	4 %

[9] Tensile testing according to. ISO 6892-1 B10, proportional test pieces, diameter of the neck area 5 mm (0.2 inch) , original gauge length 25 mm (1 inch). Results are derived from the validation data made with EOS M290 system and two powder LOTS.

[10] Solution and ageing treatments are needed in order to achieve corresponding mechanical properties. The numbers are average values determined from samples with horizontal and vertical orientation respectively.

[11] Mechanical properties depend on the thermal load of particular job layout as well as the positioning on the platform.



## Material data sheet

---

### Abbreviations

Min.	Minimum
Max.	Maximum
Approx.	Approximately
Wt.	Weight

\*Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. This also applies to applications with food contact. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

EOS<sup>®</sup>, EOSINT<sup>®</sup>, DMLS<sup>®</sup>, DirectTool<sup>®</sup> and DirectPart<sup>®</sup> are registered trademarks of EOS GmbH.

© 2022 EOS GmbH Electro Optical Systems. All rights reserved.