



## Material data sheet – FlexLine

---

### EOS MaragingSteel MS1

EOS MaragingSteel MS1 is a tool steel powder intended for processing on EOS DMLS systems.

This document provides information and data for parts built using EOS MaragingSteel MS1 powder (EOS art.-no. 9011-0016) on the following system specifications:

- EOS M400 system
- EOSYSTEM: EOSPRINT v.1.2
- EOS Parameter set MS1\_050\_FlexM400\_1.0

### Description

Parts built in EOS MaragingSteel MS1 have a chemical composition corresponding to US classification 18% Ni Maraging 300, European 1.2709 and German X3NiCoMoTi 18-9-5. This kind of steel is characterized by having very good mechanical properties, and being easily heat-treatable using a simple thermal age-hardening process to obtain excellent hardness and strength.

Parts built from EOS MaragingSteel MS1 are easily machinable after the building process and can be easily post-hardened to more than 50 HRC by age-hardening at 490 °C (914 °F) for 6 hours. In both as-built and age-hardened states the parts can be machined, spark-eroded, welded, micro shot-peened, polished and coated if required. Due to the layerwise building method, the parts have a certain anisotropy, which can be reduced or removed by appropriate heat treatment – see Technical Data for examples.

## Material data sheet – FlexLine

### Technical Data

#### Powder properties

The chemical composition of the powder (wt-%):

#### Material composition

Element	Min	Max
Fe	Balance	
Ni	17.00	19.00
Co	8.50	9.50
Mo	4.50	5.20
Ti	0.60	0.80
Al	0.05	0.15
Cr	-	0.50
Cu	-	0.50
C	-	0.03
Mn	-	0.10
Si	-	0.10
P	-	0.01
S	-	0.01

#### Max. particle size

> 63µm [1]

max 0.5 wt.-%

[1] Sieve analysis according to ASTM B214.

## Material data sheet – FlexLine

### General process data

Layer thickness	50 µm
Volume rate [2]	5.5 mm <sup>3</sup> /s (19.8 cm <sup>3</sup> /h)
[2]	The volume rate is a measure of build speed during laser exposure of the skin area. The total build speed depends on this volume rate and many other factors such as exposure parameters of contours, supports, up and downskin, recoating time and Home-In settings.

### Physical properties of parts\*

Part density [3]	8.0–8.1 g/cm <sup>3</sup>
Surface roughness as-manufactured [4]	
horizontal upskin surface	R <sub>a</sub> 9 µm; R <sub>z</sub> 60 µm
vertical surface	R <sub>a</sub> 9 µm; R <sub>z</sub> 45 µm
[3]	Weighing in air and water according to ISO 3369.
[4]	Measurement according to ISO 4287. Due to the layerwise building the roughness strongly depends on the orientation of the surface, for example sloping and curved surfaces exhibit a stair-step effect.

### Hardness in heat treated status\* [5]

Hardness Rockwell C [6]	50–56 HRC
[5]	Heat treatment procedure: Ageing temperature 490 °C (914 °F), 6 hours, air cooling
[6]	Rockwell C (HRC) hardness measurement according to EN ISO 6508-1 on polished surface



## Material data sheet – FlexLine

### Tensile data at room temperature\* [7, 8]

	As built	Heat treated [5]
Ultimate tensile strength, Rm	1200 MPa	2080 $\pm$ 100 MPa
Yield strength, Rp0.2	1070 MPa	2030 $\pm$ 100 MPa
Elongation at break A [9]	11 %	2 $\pm$ 1 %

[7] The numbers are average values and are determined from samples with horizontal and vertical orientation.

[8] Tensile testing according to. ISO 6892-1:2009 B10, proportional test pieces, diameter of the neck area 5 mm (0.2 inch) , original gauge length 25 mm (1 inch).

[9] Elongation values depends on the thermal load of particular job layout



## Material data sheet – FlexLine

---

### Abbreviations

min. minimum

max. maximum

wt. weight

\*Part properties are provided for information purposes only and EOS makes no representation or warranty, and disclaims any liability, with respect to actual part properties achieved. Part properties are dependent on a variety of influencing factors and therefore, actual part properties achieved by the user may deviate from the information stated herein. This document does not on its own represent a sufficient basis for any part design, neither does it provide any agreement or guarantee about the specific properties of a material or part or the suitability of a material or a part for a specific application.

This powder has not been developed, tested or certified as a medical device according to Directive 93/42/EEC (MDD) or Regulation (EU) 2017/745 (MDR) and is not intended to be used as a medical device, in particular for the purposes specified in Art. 2 No. 1 MDR. Insofar as you intend to use the powder as raw material for the manufacture of pharmaceutical products or medical devices (e.g. as raw material which as a material must meet the requirements of Annex 1, Chapter II MDR), the responsibility and liability for all analyses, tests, evaluations, procedures, risk assessments, conformity assessments, approval and certification procedures as well as for all other official and regulatory measures required for this purpose shall lie solely with you both with regard to the pharmaceutical product and/or medical device manufactured by you and with regard to the properties, suitability, testing, evaluation, risk assessment, other requirements for use of the powder as raw material. This also applies to applications with food contact. In this respect, the limitations of liability pursuant to our General Terms and Conditions and the system sales or material contracts shall apply.

EOS<sup>®</sup>, EOSINT<sup>®</sup>, DMLS<sup>®</sup>, DirectTool<sup>®</sup> and DirectPart<sup>®</sup> are registered trademarks of EOS GmbH.

© 2022 EOS GmbH Electro Optical Systems. All rights reserved.